


### Intended use

Thixotropic glossy synthetic paint with long open time to coat by brush or roller components and constructions which are made of wood or metal. For interior and exterior use.

### Processing instructions



#### Mixing ratio

hardener

by weight (lacquer : hardener)

by volume (lacquer : hardener)

--

--

--



#### Hardener

--



#### Pot life

2 days with Mipa Härterverdünnung



#### Thinner

Mipa KH-Verdünnung

MipaTerpentinersatz

Mipa Härterverdünnung



#### Spray viscosity

gravity spray gun

Airmix/Airless

20 - 25 s 4 mm DIN

30 - 40 s 4 mm DIN



#### Application mode

application mode

hardener

pressure  
(bar)

nozzle (mm)

spray  
passes

dilution

gravity spray gun /  
HVLV

--

2,0 - 2,5

1,5 - 1,8

2 - 3

20 - 25 %

Airmix / Airless

--

100 - 120

0,23 - 0,28

1

10 - 15 %

paint brush, roller\*

--

--

--

--

0 - 10 %

\*suitable : Mipa KH-Verdünnung, Terpentinersatz; unsuitable: Mipa Härterverdünnung



#### Drying time

hardener

object  
temperature

dust dry

set to  
touch

ready for  
assembly

sandable

recoatable

--

20 °C

60 - 70 min

6 - 8 h

24 h

--

24 h

--

60 °C

--

--

60 min

--

--

Fully cured after 8 - 10 days (at 20 °C).

### Note

---

<b>Characteristics:</b>	binder base: alkyd resin solids content (% by weight): 62 - 67 solids content (% by volume): 55 - 56 delivery viscosity DIN 53211 4 mm (in s): thixotropic density DIN EN ISO 2811 (kg/l): 1,0 - 1,2 gloss level ISO 2813 at 60° (GU): > 80 gloss
<b>Properties:</b>	long open time, excellent filling properties, good edge coverage highly UV- and weather-resistant resistant to petrol and diesel if exposed temporarily short-term heat exposure 140 °C permanent heat exposure 120 °C
<b>Theoretical spreading rate :</b>	43,4 - 50,1 m <sup>2</sup> /kg for 10 µm dry film thickness 50,5 - 51,3 m <sup>2</sup> /l for 10 µm dry film thickness
<b>Storage:</b>	for at least 3 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.
<b>VOC Regulation :</b>	EU limit value according to Directive 2004/42/EC for this product (category B/d) : 420 g/l This product contains the following maximum VOC-values: applied by brush/ roller: < 420 g/l of VOC
<b>Processing conditions:</b>	from + 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.
<b>Substrate preparation:</b>	Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating!  Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original metal substrate.  steel: - blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly - de-rust with hand and power tools to degree of cleanliness St 3 - degrease with Mipa WBS Reiniger or Mipa Silikonentferner  wood (max. moisture: 15 %): - pre-sanding with sandpaper P 180 - P 280 and dust off thoroughly
<b>Proposed coating structure:</b>	steel: priming coat: *AK 100-20 / AK 105-20 with 50 - 60 µm dry film thickness finishing coat: AK 250-90 with 50 - 60 µm dry film thickness  wood in exterior use: waterproofing: Mipaxyl spezial priming coat: Mipa Malervorlack HS with 50 - 60 µm dry film thickness finishing coat: AK 250-90 with 50 - 60 µm dry film thickness  wood in interior use: priming coat: Mipa Malervorlack HS with 50 - 60 µm dry film thickness finishing coat: AK 250-90 with 50 - 60 µm dry film thickness

**Special notes:**

For professional use only.

Applying too thick layers may extend considerably the drying time.

Permanent thermal stress may lead to yellowing.

Check colour shade prior to application

**Cleaning of tools:**

Clean tools immediately after use with Mipa Nitroverdünnung.